

Technical data sheet

Requirements according to report number 388 Norwegian Public Roads Administration

Declaration of Conformity

Our spacers made of fibre concrete with the mixture "PremiumMix CD" fulfill the following characteristics.

Technical characteristics

Description	Requirements report no 388
height deviation for spacers	± 2 mm
deformation	< 1 mm
heat load	< 2 mm
breaking load*	> 6 kN
maximum particle size	$D < 1/4$ of the height of the spacer
water/cement ratio	$\leq 0,4$
content of silica fume	> 5% rcw
water absorption after 30 minutes	5.0%
water absorption after 24 hours	8.5%

* 6kN applies only for special cut width for 30mm spacers

Recommendations with regard to product application given in the present technical data sheet for practical assistance of product users are based on our experience and our present scientific and practical body of knowledge. These recommendations, however, are given without engagement and do not establish a contractual relationship or subsidiary duties. These recommendations do not relieve users of their liability and of their own responsibility to test, whether our product is adequate for the intended purpose of application.