

Technical Data Sheet

Trennfit Super

Formwork oil for all types of formwork

The concrete release agent **Trennfit** is the right product for all formwork types and areas of application. An excellent release effect can be guaranteed.



Product

Description	Trennfit Super is a ready-to-use, physically and chemically acting concrete release agent based on mineral oil, free of solvents and silicone.					
	Its chemical functionality is based on a reaction of calcium hydroxide and aluminium hydroxide of the concrete and conventionally physically due to its water-repellent properties. This facilitates the sliding of air and water bubbles during concreting, which counteracts blowhole formation. In addition, concrete adhesion to the formwork is strongly reduced, which ensures easy demoulding and prevents concrete residues from sticking to the formwork. This protects the formwork and diminishes the cleaning effort for the formwork.					
	Trennfit Super is used for fair-faced concrete, textured concrete and white concrete, where special attention is paid to an even concrete surface. In addition, Trennfit Super is excellently suited for formwork in precast concrete production with heated and unheated formwork.					
Usage	Trennfit Super is recommended for all concrete structures, exposed concrete and also for subsequent coating of the concrete surfaces or plaster and stucco work.					
	Trennfit Super is suitable for all formwork types (board formwork, coated formwork panels, plastic formwork, steel formwork, etc.).					
	Trennfit Super is particularly suitable for long-term preservation of steel formwork.					
	In addition, Trennfit Super is excellently suited for the maintenance of machines and equipment due to its rust protection properties.					
Characteristics /	 best adhesion of subsequent coatings and plasters to the concrete 					
advantages	 no chalking of the concrete surface when used as directed 					
	 economical in use - 1 l is sufficient for up to 100 m² of steel formwork 					
	 Complies with DBV-guidelines for release agents 					
Test Reports						
Approvals / Standards	Not required					

MAX FRANK Group

Max Frank GmbH & Co. KG | Mitterweg 1 | 94339 Leiblfing | Germany | info@maxfrank.com



Product Data					
Appearance	Yellow-ish liquid				
Packaging	 can: 30 l barrel: 200 l 				
Storage	frost-resistant, down to -30°C				
Material Properties	Form: Colour:	liquid yellow-ish			
	Odour: Kinematic viscosity:	low odour approx. 7,5 mm²/s at 40°C			
	Density:	approx. 0,88 g/ccm at 15°C			
	Basis:	Napthenic, paraffinic mineral oils, containing additives			
	Solubility:	insoluble in water			
	Shelf life:	1 year in closed original recipient			
	WGK: (Water hazard class)	1, i.e. slightly hazardous to water			
Processing	Trennfit Super is ready for use and must not be diluted. Formwork surfaces must be clean and dry.				
	Trennfit Super is applied thinly and evenly covering with the MAX FRANK special sprayer. Application with a brush, cloth or similar is also possible, but the consumption quantities and labour costs are considerably higher. Please note that puddles of excess release agent and lack of release agent due to excessively absorbent formwork must be avoided.				
	New wooden boarding is best pre-treated with cement stillage due to its wood sugar precipitation and then sprayed with Trennfit Super .				
Consumption quantities	1 litre Trennfit Super is sufficient for:				
Consumption quantities					
Consumption quantities	Ca. 80 – 100 m² st	r is sufficient for: eel formwork			
Consumption quantities	Ca. 80 – 100 m² st Ca. 10 – 20 m² sr	eel formwork moothened concrete formwork			
Consumption quantities	Ca. 80 – 100 m² st Ca. 10 – 20 m² sr Ca. 20 – 30 m² rc	eel formwork moothened concrete formwork bugh wood			
Consumption quantities	Ca. 80 – 100 m² st Ca. 10 – 20 m² sr Ca. 20 – 30 m² rc Ca. 30 – 40 m² pl	eel formwork moothened concrete formwork ough wood aned wood			
Consumption quantities	Ca. 80 – 100 m² st Ca. 10 – 20 m² sr Ca. 20 – 30 m² rc Ca. 30 – 40 m² pl	eel formwork moothened concrete formwork bugh wood			
Consumption quantities	Ca. $80 - 100 \text{ m}^2$ st Ca. $10 - 20 \text{ m}^2$ sr Ca. $20 - 30 \text{ m}^2$ rc Ca. $30 - 40 \text{ m}^2$ pl Ca. $70 - 90 \text{ m}^2$ co Not classified ac	eel formwork moothened concrete formwork bugh wood laned wood pated formwork panel ccording to the ordinance on Hazardous Substances			
	Ca. $80 - 100 \text{ m}^2$ st Ca. $10 - 20 \text{ m}^2$ sr Ca. $20 - 30 \text{ m}^2$ rc Ca. $30 - 40 \text{ m}^2$ pl Ca. $70 - 90 \text{ m}^2$ cc Not classified ac No dangerous g	eel formwork moothened concrete formwork bugh wood aned wood bated formwork panel coording to the ordinance on Hazardous Substances goods according to UN, IMO, ADR/RID and IATA/ICAO			
	Ca. $80 - 100 \text{ m}^2$ st Ca. $10 - 20 \text{ m}^2$ sr Ca. $20 - 30 \text{ m}^2$ rc Ca. $30 - 40 \text{ m}^2$ pl Ca. $70 - 90 \text{ m}^2$ cc Not classified ac No dangerous g Water hazard cl	eel formwork moothened concrete formwork bugh wood laned wood bated formwork panel ccording to the ordinance on Hazardous Substances loods according to UN, IMO, ADR/RID and IATA/ICAO ass I, i.e. slightly hazardous to water			
	Ca. 80 – 100 m ² st Ca. 10 – 20 m ² sr Ca. 20 – 30 m ² rc Ca. 30 – 40 m ² pl Ca. 70 – 90 m ² cc Not classified ac No dangerous g Water hazard cl Waste disposal	eel formwork moothened concrete formwork bugh wood laned wood bated formwork panel ccording to the ordinance on Hazardous Substances poods according to UN, IMO, ADR/RID and IATA/ICAO ass I, i.e. slightly hazardous to water key:			
	Ca. 80 – 100 m ² st Ca. 10 – 20 m ² sr Ca. 20 – 30 m ² rc Ca. 30 – 40 m ² pl Ca. 70 – 90 m ² cc Not classified ac No dangerous g Water hazard cl Waste disposal Product:	eel formwork moothened concrete formwork bugh wood laned wood bated formwork panel ccording to the ordinance on Hazardous Substances loods according to UN, IMO, ADR/RID and IATA/ICAO ass I, i.e. slightly hazardous to water			

MAX FRANK Group

Max Frank GmbH & Co. KG | Mitterweg 1 | 94339 Leiblfing | Germany | info@maxfrank.com



Environment / Sustainability	The company MAX FRANK GmbH & Co. KG has implemented a certified environmental management system since July 2022.		
,	Please dispose of and recycle the packaging in accordance with the applicable legal regulations.		
Ecological quality	Concrete release agents that are used in the construction of concrete building components are classified within the DGNB system in the area "Ecological quality".		
	An assessment is carried out in quality levels depending on the GISCODES. The higher the quality level, the more positive the influence on a high degree of fulfilment in this category.		
	The designation Giscode stands for "Hazardous Substance Information System Code" and was developed by the "Berufsgenossenschaften der Bauwirtschaft (BG Bau)". It is a labelling system in which products with comparable health hazards are grouped together.		

Quality levels for formwork oils/concrete release agents

GISCODE	Quality level 1	Quality level 2	Quality level 3	Quality level 4	Product group
BTM 01					Concrete emulsions, non-labelled
BTM 05					Concrete release emulsions, containing preservatives
BTM 10	Trennfit Pure	Trennfit Pure	Trennfit Pure		Concrete release agent, non- labelled
BTM 15	Trennfit Pure	Trennfit Pure			Concrete release agent emulsions, allergy hazard due to preservatives
BTM 20	Trennfit Trennfit Super Trennfit Pure				Concrete release agent, low viscosity

Disclaimer / Notes:

The usability of the products in the specific installation situation must be checked by the user. This data sheet is constantly updated. Technical changes are therefore expressly reserved without prior information of the customer. The currently valid version can be found on our website at: www.maxfrank.com. Our General Terms and Conditions of Sale apply in addition.

MAX FRANK Group

Max Frank GmbH & Co. KG | Mitterweg 1 | 94339 Leiblfing | Germany | info@maxfrank.com